

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : A61C 8/00	A1	(11) International Publication Number: WO 94/09717 (43) International Publication Date: 11 May 1994 (11.05.94)
<p>(21) International Application Number: PCT/SE93/00871</p> <p>(22) International Filing Date: 25 October 1993 (25.10.93)</p> <p>(30) Priority data: 9203184-8 28 October 1992 (28.10.92) SE</p> <p>(71) Applicant (for all designated States except US): AKTIEBOLAGET ASTRA [SE/SE]; S-151 85 Södertälje (SE).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only) : HANSSON, Stig, Gustav, Vilhelm [SE/SE]; Gåsmossen 32, S-436 00 Askim (SE). HOLMEN, Anders [SE/SE]; Doktorsvägen 7, S-436 50 Hovås (SE).</p> <p>(74) Agent: KALLING, Sven; AB Astra, Patent Department, S-151 85 Södertälje (SE).</p>		<p>(81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, UA, US, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>
<p>(54) Title: FIXTURE IN A DENTAL IMPLANT SYSTEM</p> <div data-bbox="732 1239 997 1730" style="text-align: center;"> </div>		
<p>(57) Abstract</p> <p>The invention relates to a fixture (1, 10) in a dental implant system having an outer end provided with a conically flaring portion (10) intended to at least partly abut the bone tissue. The outer side of the conically flaring portion (10) is provided with a circumferentially oriented, defined micro-roughness (9) having a height which may vary between 0.02 and 0.20 mm.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

Fixture in a dental implant system.

5 The present invention relates to fixtures for dental implants, i. e. the parts of dental implant systems which are to be implanted in the bone tissue, and particularly to fixtures whose outer end or neck are provided with a conically flaring portion intended to at least partly abut the bone tissue.

10 Background to the invention

15 Fixtures having a cylindrical main body and a conically flaring upper portion or neck have been known and used in the art of dental implants for a long period of time. These fixtures are to be inserted into bore-holes in the jaw-bone in order to become osseointegrated to the bone tissue. The cylindrical parts generally osseointegrate correctly provided the proper techniques are used.

20 There are however some difficulties regarding the osseointegration around the conical neck portion of the implants which portion normally is smooth or polished. For some reason the bone tissue may degenerate around a smooth or polished conical part (bone resorbtion),
25 leaving a pocket in the bone tissue around the conical part. The mechanism behind this is not quite clear. These pockets normally are accepted as inevitable although it is not entirely satisfactory that not the entire implant is osseointegrated, particularly since
30 this pocket is formed in the strongest part of the bone tissue, the cortical bone.

Short description of the inventive concept

35 It surprisingly has been found that the provision of a circumferentially or tangentially oriented, defined micro-roughness on the outer side of the conically flaring portion of the fixture having a height which

may vary between 0.02 and 0.20 mm alleviates this problem, the risk for pockets in the bone tissue around the conically flaring portion being minimized.

- 5 In preferred embodiments the micro-roughness, as set forth in the appended dependent claims, may be in the form of circumferential beads or microthreads.

Short description of the appended drawings

10

Fig 1 shows the exterior of a fixture according to the invention,

Fig 2 shows the fixture in fig 1, partly sectioned.

15

Detailed description of a preferred embodiment of the invention

- 20 In the description below, the invention is illustrated by means of micro-threads. It should be noted that the description in the relevant parts (i. e. the parts not relating directly to the helical nature of the threads) also is applicable to the embodiment featuring the circumferential beads and that this choice does not
- 25 reflect any preference regarding the two embodiments.

- Thus, in a preferred embodiment, the invention comprises an implant or fixture having a generally cylindrical body 1 for insertion into a bore-hole into
- 30 bone tissue. The envelope surface of the body 1 is provided with conventional threads 2. These threads will allow the implant to function as a screw. The forward end or the tip of the screw is provided with three cutting edges 4 together with chip-collecting
- 35 cavities 3.

The cutting edges 4 and the chip-collecting cavities 3 will allow the screw, if necessary, to function as a self-tapping screw for cutting new threads or adjusting already cut threads in the tissue.

5

The other end of the screw is, as is quite conventional in the art, provided with a longitudinal bore for the attachment of an abutment for bridging the soft tissue covering the bone tissue and for the attachment of a prosthesis. The inner part 7 of the bore is cylindrical and provided with interior threads 6 and the outer part 5 of the bore, which is located in a conically flaring portion 10) is conically flaring in order to accommodate a conically tapering attachment part of an abutment. The transitional portion between the conical part and the cylindrical bore comprises a hexagonal socket 8 which is intended to cooperate with a corresponding, hexagonal part of the abutment in order to allow the abutment to be oriented and locked in specific rotational positions relative to the fixture.

As can be seen in Figs 1 and 2, the outer side of the conically flaring portion 10 is provided with threads serving as oriented micro-roughness. The threads may be 0.1 mm high and the distance to the adjacent thread (crest to crest) may be 0.2 mm. The threads are here called microthreads (and the beads microbeads) since their height and distance from each other are in the micrometer range. The microthreads may be multiple-threaded, for instance triple-threaded which means that the pitch of the thread would be 0.6 mm. The angle between the flanks of a microthread may for instance be 45° or 60°. The microthreads have a rounded design in order to avoid, or at least minimize, stress-concentrations in the bone tissue around the microthreads.

Generally, the height of the microthreads may be within the range of 0.02 - 0.20 mm. In a preferred embodiment the height may vary between 0.02 and 0.15 mm, in a more preferred embodiment between 0.05 and 0.15 and in a most preferred embodiment, described above, the height is 0.1 mm. The number of threads is optional but may for instance vary between 1 and 5.

The microthreads can be regarded as a defined, oriented roughness being in the same size range as the kind of prior art non-oriented surface roughness, which for instance may be obtained by plasma-spraying (a conventional technique for obtaining a surface roughness on implants). A non-oriented roughness having smaller dimensions, for instance obtained by blasting, may be superimposed on the microthreads.

New bone tissue will rapidly grow into the microthreads due to the low height of the threads and a retention which is considerably better in the axial direction than in the rotational (tangential) direction will be obtained relatively fast. This of course is a result of the threads being oriented circumferentially.

It would seem that the positive results obtained by this design may be explained as follows:

When the bone tissue has grown into the spaces between individual projections of the micro-roughness, the axial loads on the implant may be transmitted in an axial direction (related to the axial direction of the fixture) to the bone tissue around the conical portion in a biomechanically correct way, i. e. in such a way that the bone tissue is stressed correctly around the conical part and that bone resorbtion consequently does not occur.

Above, the fixture has been described as having normal threads on the cylindrical main body. It may however be particularly advantageous if both the main body and the conically flaring part is provided with microthreads, since this will allow the fixture to be used both as a fixture which gently can be tapped or pushed into the bore-hole and as a fixture which easily can be screwed into, or unscrewed from, the bore-hole.

It should be emphasized that the invention is not limited to the embodiments described above and can be varied in many ways within the scope of the appended claims.

CLAIMS

1. Fixture (1, 10) in a dental implant system having an outer end provided with a conically flaring portion (10) intended to at least partly abut the bone tissue, characterized in that the outer side of the conically flaring portion (10) is provided with a circumferentially oriented, defined micro-roughness (9) having a height which may vary between 0.02 and 0.20 mm.
2. Fixture according to claim 1, characterized in that said micro-roughness has a height between 0.02 and 0.15 mm.
3. Fixture according to claim 2, characterized in that said micro-roughness has a height between 0.05 and 0.15 mm.
4. Fixture according to any one of claims 2 or 3, characterized in that said micro-roughness has a height of 0.1 mm.
5. Fixture according to claim 1, characterized in that the defined micro-roughness is in the form of circumferential beads.
6. Fixture according to claim 1, characterized in that the defined micro-roughness is in the form of a microthread (9).
7. Fixture according to anyone of claims 2 - 4, characterized in that the distance between adjacent threads or beads, crest to crest, is twice the height of the threads or beads.





FIG 1

FIG 2



INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 93/00871

A. CLASSIFICATION OF SUBJECT MATTER

IPC5: A61C 8/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC5: A61C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP, A1, 0388576 (INSTITUT STRAUMANN AG), 26 Sept 1990 (26.09.90) --	1
A	WO, A1, 9205745 (AKTIEBOLAGET ASTRA), 16 April 1992 (16.04.92) -- -----	1



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

25 January 1994

Date of mailing of the international search report

02 -02- 1994

Name and mailing address of the ISA/

Swedish Patent Office

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Authorized officer

Jack Hedlund

Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

Information on patent family members

30/12/93

International application No.

PCT/SE 93/00871

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
EP-A1-	0388576	26/09/90	JP-A-	3047264	28/02/91
WO-A1-	9205745	16/04/92	AU-A-	8663691	28/04/92
			CA-A-	2093517	09/04/92
			EP-A-	0552261	28/07/93